

TECHNICAL DATA - PETG
 CLEAR

MATERIAL PROPERTIES	STANDARD	UNIT	VALUE
DENSITY	ISO 1183	g/cm ³	1.27
WATER ABSORPTION (@23 °C / 50%RH)	ISO 62	%	0.2
REFRACTIVE INDEX 20DEG C	ISO 489		1.567
MECHANICAL			
TENSILE STRESS AT BREAK	ISO 527	MPa	>45
MODULUS OF ELASTICITY	ISO 527	N/mm ²	2020
IMPACT STRENGTH	DIN 53453	(kJ/m ²)	>45
NOTCHED IMPACT STRENGTH	DIN 53453	(kJ/m ²)	7
BALL INDENTATION HARDNESS	ISO2039-1	(N/mm ²)	202
SHORE HARDNESS	DIN 53505	-	R105
THERMAL			
MELTING POINT	DIN5376	°C	170
COEFFICIENT OF LINEAR THERMAL EXPANSION (23-60 °C)	ISO 11359	m/(m-K) 5*10 ⁻⁵	
MAX WORK TEMP	-	°C	65
MAX BRIEF TEMP	-	°C	80
MIN TEMP	-	°C	- 30
FLAMMABILITY OXYGEN INDEX UL94 (6MM)	4589	%	26 V2
ELECTRICAL			
DIELECTRIC CONSTANT	DIN 53483	@50HZ DRY	2.6
VOLUME RESISTIVITY	DIN 53482	Ohm*cm	>10 ¹⁵
SURFACE RESISTIVITY	DIN 53482	Ohm	>10 ¹⁶
TRACKING RESISTANCE	DIN 53480		-
DIELECTRIC STRENGTH	DIN 53481	kV/mm	>20
PHYSIOLOGICAL			
FOOD CONFORMITY TO			
EU		YES	
FDA		YES	

The electrical properties as stated result from measurements on natural, dry material. With other colours (in particular Black) or saturated material, there may be a clear difference in the electrical properties.

All information given is in good faith and without warranty

RM1407,Platinum Hotel,BaoMin No.1 Road,BaoAn District,ShenZhen City,China

Tel: +86 0755 26098435 Fax: +86 0755 82320135

Email: market@sinoeng.cn